



## INVEBI coatings Italy – Technical Data Sheet

### 1281 FONDALAC WHITE IV132/BCO Catalyst at 50%

<b>Product:</b>	Pigmented polyurethane base coat
<b>Description:</b>	Two component pigmented base coat; good sanding, excellent resistance to over coating and good verticality.
<b>Support Type:</b>	MDF or wood

<b>Characteristics:</b>  <b>Flash Point:</b> <b>Please refer to the SDS</b>  <b>Specific Weight:</b> <table border="1" style="width: 100%;"> <tr> <td>A = 1.545</td> </tr> <tr> <td>B = 0.920</td> </tr> </table>	A = 1.545	B = 0.920	1. Viscosity Ford 4 at 30°C	• 65 sec +/- 5 sec
	A = 1.545			
	B = 0.920			
	2. Viscosity Ford 4 at 30°C after catalysis	• /		
	3. Solid Content A	• 72% +/- 1%		
	4. Solid Content B	• 26% +/- 1%		
	5. Solid Content A + B	• 57% +/- 1%		
	6. Pot Life (100 gr/30°C)	• 4 hr		
	7. Practical Useful Life at 30°C	• 2 hr		
	8. Dust Free at 30°C after	• 20 min		
	9. Touch Dry at 30°C after	• 1 hr		
	10. Dry in Deepness at 30°C after	• 6 hr		
11. Forced Dry 40-45°C after	• /			
12. Light Stability	• /			

<b>Application:</b>	By spray or by curtain coater
---------------------	-------------------------------

<b>Using Method:</b>	1281 FONDALAC WHITE	100	Parts in Ltr/KG
	IV132/BCO	50	Parts in Ltr/KG
	Thinner 106	30 – 50	On Part A

<b>Quantity to be Applied:</b>	120 – 180 gr/sqm
<b>Sanding:</b>	After 4 hours
<b>Over-coating:</b>	With NC or PU top coat

<b>Storage:</b>	Part A, at 25°C	8 months	in the original sealed packing
	Part B, at 25°C	6 months	in the original sealed packing

<b>General Notes:</b>	Always mix the products well before use
-----------------------	---