

Product Description

Air-drying type polyurethane-alkyd resin based enamel varnish

Recommended Use

Suitable for use as decorative and protective coating for interior and exterior wood surfaces

Features

Fast dry
Easy application
Excellent abrasion resistance

Physical Characteristics

| Recommended Application Data | Dry Film Thickness (µm) | Theoretical Coverage (m ² /l) |
|------------------------------|-------------------------|--|
| | 20 µm | 10 m ² /l |
| Specific Gravity | 0.85 – 0.95 | |
| Flash Point | 35 °C | |
| Finish | Gloss / Matt | |
| Color Range | Clear | |
| Standard Packing Size | 1 L / 5 L | |
| Shelf Life | 12 months | |

Application Method

| | |
|-----------------|-----------------------------------|
| Brush or Roller | Recommended method of application |
| Thinning Ratio | 20 – 40 % by weight |

Drying Time

| Touch Dry | Hard Dry | Overcoating Interval | |
|-----------|----------|----------------------|----------------|
| | | Minimum | Maximum |
| 1 hour | 3 hours | 6 hours | Not applicable |

Useful Information

| | |
|----------|--|
| Thinner | APM TT 500 Thinner |
| Cleaner | APM TT 500 Thinner |
| Storage | Store in a cool shaded dry area |
| Disposal | Always keep container in a secure upright position. Use sand to contain any spillage. Dispose of paint in accordance with the appropriate Environmental Quality Regulations. |

Surface Preparation

Timber Flooring :

Ensure floor is acclimatized to its end-use environment.
The surface which is to be coated must be sanded back to bare wood, dry and free from sanding dust, oil, wax and other contamination. A Sanding Disc or Screen grit of 120 should be used for the final sanding of the wood.
Vacuum or clean the surface with cloth.
Add in the required amount of thinner and stir the product thoroughly before use.
Apply 1st coat of S260 PU Varnish evenly on the surface. Allow it to dry for 6 hours.
Sand the coated surface along the grains Patten with 240 grit sand paper.
Apply 2nd coat of S260 PU Varnish evenly on the surface. Allow it to dry for 6 hours.
Sand the coated surface along the grains Patten with 320 grit sand paper.
Apply 3rd coat of S260 PU Varnish evenly on the surface. Allow it to dry for 6 hours.

Coating Specifications

| 1 st Coat | 2 nd Coat | 3 rd Coat | |
|------------------------|------------------------|------------------------|--|
| APILAC S260 PU Varnish | APILAC S260 PU Varnish | APILAC S260 PU Varnish | |

Notes

The coating specifications provided above are typical. For specific recommendations to suit individual applications, please refer to your Asia Paint Representative.
Stir the product well before use.

Safety Precaution

Avoid contact with eyes and skin. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves.
Do not use in poorly ventilated areas, do not breathe in vapor or spray mist.
This product is flammable. Keep away from sources of ignition. Do not smoke. Take precautionary measures against static discharge.
In case of fire, use carbon dioxide, normal foam or dry agent.

First Aid

| | |
|--|--|
| Eyes | Wash off in flowing water or shower |
| Skin | Flush with plenty of water |
| Inhalation | Remove to fresh air, loosen collar and keep patient rested |
| Ingestion | If swallowed, seek medical attention. Do not induce vomiting unless directed to do so by medical personnel |
| For further safety information, please refer to our Safety Data Sheet (SDS) | |

Disclaimer

The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he wishes to use it. As we have no control over the treatment of the product, the standard of surface preparation of the substrate, or other factors affecting the use of this product, we are not responsible for its performance, nor would we accept any liability whatsoever or howsoever arising from the use of this product unless specifically agreed to in writing by us. The information contained in this data sheet may be modified by us from time to time, and without notice, in light of our experience and product development.