GF 8221

Ver 2.00 updated 2025

# Product Description

Acrylic modified nitro-cellulose lacquer

## Recommended Use

Suitable for finishing or touching up of wood, metal, or objects which requires a fine finish

### **Features**

Good applicability Excellent adhesion

## Physical Characteristics

Recommended Application Data	Dry Film Thickness (μm)	Theoretical Coverage (m²/l)
	10 – 30 μm	Depends on surface and thickness
Specific Gravity	0.82 ± 0.02	
Flash Point	-41 °C	
Finish	High Gloss, Semi-Gloss, Matt	
Color Range	Refer to Color Card. Other colors available upon request	
Standard Packing Size	400 c.c.	
Shelf Life	24 months	

# Application Method


Spray Can	To apply an even coat, sweep the can horizontally and vertically past the object as you spray
Thinning Ratio	Not Applicable

# **Drying Time** At 30°C

Touch Dry	Hard Dry	Overcoating Interval	
		Minimum	Maximum
15 minutes	2 hour	3 hours	Not applicable

## Useful Information

Thinner	Not Applicable
Cleaner	Suitable commercial lacquer thinner
Storage	Store in a cool shaded dry area
Disposal	Always keep container in a secure upright position. Use sand to contain any spillage. Dispose of paint in accordance with the appropriate Environmental Quality Regulations.
Other	Ozone friendly DME gas is used as propellant









Add: 20 Tuas Avenue 8 Singapore 639235 Tel: (65) 6546 3955 Fax: 6546 3855 E-mail: <a href="mailto:sales@asiapaintsingapore.com">sales@asiapaintsingapore.com</a> Website: <a href="mailto:www.asiapaintsingapore.com">www.asiapaintsingapore.com</a>

GF 8221

Ver 2.00 updated 2025

## Surface Preparation

The service and life span and the service performance of paints are directly related to the degree of surface preparation.

The surface to be overcoated must be dry and free from surface contaminants.

Remove all oil, wax and grease by solvent cleaning.

Remove all soluble salts by washing with fresh water.

Remove all dirt and dust by dry brushing.

Remove all loose flaking coatings, rust and mill scale by sanding / grinding, chipping, needle gun or spot blasting.

# **Coating Specifications**

1 <sup>st</sup> Coat		
LUCKU Aerosol		

### **Notes**

The coating specifications provided above are typical. For specific recommendations to suit individual applications, please refer to your Asia Paint Representative.

Shake the product well before use.

Contents under pressure. Not recommended for air freight.

### Safety Precaution

Avoid contact with eyes and skin. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves.

Do not use in poorly ventilated areas, do not breathe in vapor or spray mist.

This product is flammable. Keep away from sources of ignition. Do not smoke. Take precautionary measures against static discharge.

In case of fire, use carbon dioxide, normal foam or dry agent.

Contents under pressure. Do not burn, puncture or compress.

Empty the cans before disposal.

#### First Aid

Eyes	Wash off in flowing water or shower
Skin	Flush with plenty of water
Inhalation	Remove to fresh air, loosen collar and keep patient rested
Ingestion	If swallowed, seek medical attention. Do not induce vomiting unless directed to do so by medical personnel

For further safety information, please refer to our Safety Data Sheet (SDS)

#### Disclaimer

The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he wishes to use it. As we have no control over the treatment of the product, the standard of surface preparation of the substrate, or other factors affecting the use of this product, we are not responsible for its performance, nor would we accept any liability whatsoever or howsoever arising from the use of this product unless specifically agreed to in writing by us. The information contained in this data sheet may be modified by us from time to time, and without notice, in light of our experience and product development.





