



Asia Paint (Singapore) Pte Ltd

20, Tuas Ave 8
Singapore 639235
Tel: (65) 6546 3955 Fax: (65) 6546 3855
E-mail: sales@asiapaintsingapore.com

“EKOLAC” 1600 WATERBASED PU ENAMEL

DESCRIPTION	:	Air drying type Water-based Urethane Lacquer for decoration and protection of interior and exterior building surface. Having been awarded the Green Label by the Singapore Environmental Council is a testament that our products eco-friendliness and quality meet international standards.																								
USE	:	Suitable for wood, prepared concrete, plaster, mortar, asbestos, cement board and the old existing paint film. It is recommended for use in office, schools, hospitals and shopping mall etc.																								
FEATURES	:	<ul style="list-style-type: none">* Easy application and fast drying* Low VOC, low odor* No fire hazard* Resist against alkali and water* Excellent weathering resistance																								
FINISH	:	Low sheen appearance																								
COLOUR	:	Clear and white, other colours are available upon request																								
TECHNICAL DATA.	:	<table><tr><td>Packing</td><td>:</td><td>5 Litres or 20 Litres</td></tr><tr><td>Specific Gravity</td><td>:</td><td>1.0 – 1.30 depending on colour</td></tr><tr><td>Shelf Life</td><td>:</td><td>12 months</td></tr><tr><td>Flash Point</td><td>:</td><td>>68 °C</td></tr></table>	Packing	:	5 Litres or 20 Litres	Specific Gravity	:	1.0 – 1.30 depending on colour	Shelf Life	:	12 months	Flash Point	:	>68 °C												
Packing	:	5 Litres or 20 Litres																								
Specific Gravity	:	1.0 – 1.30 depending on colour																								
Shelf Life	:	12 months																								
Flash Point	:	>68 °C																								
APPLICATION DATA	:	<table><tr><td>Application Method</td><td>:</td><td>Brush or roller</td></tr><tr><td>Thinner</td><td>:</td><td>Water</td></tr><tr><td>Thinning Ratio</td><td>:</td><td>Ready for use. If thinning is necessary, not more than 10% by weight.</td></tr><tr><td>Spreading Rate</td><td>:</td><td>6-8 m²/ltr/coat</td></tr><tr><td>No. of Coatings</td><td>:</td><td>1 – 3 Coats</td></tr><tr><td>Drying Time</td><td>:</td><td>1 hour at 30 °C</td></tr><tr><td>Overcoating Interval</td><td>:</td><td>Minimum 3 hours between each coat</td></tr><tr><td>Clean Up</td><td>:</td><td>By water</td></tr></table>	Application Method	:	Brush or roller	Thinner	:	Water	Thinning Ratio	:	Ready for use. If thinning is necessary, not more than 10% by weight.	Spreading Rate	:	6-8 m ² /ltr/coat	No. of Coatings	:	1 – 3 Coats	Drying Time	:	1 hour at 30 °C	Overcoating Interval	:	Minimum 3 hours between each coat	Clean Up	:	By water
Application Method	:	Brush or roller																								
Thinner	:	Water																								
Thinning Ratio	:	Ready for use. If thinning is necessary, not more than 10% by weight.																								
Spreading Rate	:	6-8 m ² /ltr/coat																								
No. of Coatings	:	1 – 3 Coats																								
Drying Time	:	1 hour at 30 °C																								
Overcoating Interval	:	Minimum 3 hours between each coat																								
Clean Up	:	By water																								
PAINTING SPECIFICATION	:	Surface Preparation : Remove Oil, grease and foreign matters before coating. If necessary, prepare by sanding to establish a smooth clean surface.																								

